

## TYPE 302 STAINLESS STEEL WIRE – NICKEL COATED

Type 302 stainless steel wire is a general purpose Stainless alloy typically composed of 18% Chromium and 8% nickel. The balance of the chemistry is: carbon 15% maximum, manganese 2.00% maximum: and silicon 1.00% maximum. It is the most widely used stainless spring wire because of its high corrosion resistance properties and good tensile strength. For spring applications it is generally furnished in the cold drawn condition, with tensile strengths as shown in the table below. The tensile strength for straightened and cut wire may be reduced by 10% from the figures shown on the table.

Nickel coated stainless steel wire was developed to have excellent lubrication to minimize friction during the coiling process. The consistent and uniform lubrication helps provide stable spring dimensions and less load variation during coiling. Nickel coated stainless wire eliminates the need for pickling and degreasing prior to heat treatment with no major color change expected after heat treatment, retaining its same bright and consistent finish.

Gibbs Type 302 stainless steel wire is available in the size range .006" to .125". All wire conforms to ASTM-A-313 and AMS-5688

Chemical Composition per ASTM-A-313								
Carbon	.12% max		Sulfur	.030% max		Molybdenum	0.75% max	
Manganese	2.00% max		Chromium	17.00 - 19.00 %		Copper	0.75% max	
Phosphorus	.045% max		Nickel	8.00 – 10.00 %				
Silicon	1.00% max		Nitrogen	.10% max				

  

Tensile Strength Table ( ASTM-A-313) *KSI								
Over	To	Tensile *	Over	To	Tensile*	Over	To	Tensile*
.001	.008	325-355	.031	.034	282-310	.125	.136	217-248
.009	.010	320-350	.034	.037	280-308			
.010	.011	318-348	.037	.041	275-304			
.011	.012	316-346	.041	.045	272-300			
.012	.013	314-344	.045	.050	267-295			
.013	.014	312-342	.050	.054	265-293			
.014	.015	310-340	.054	.058	261-289			
.015	.016	308-338	.058	.063	258-285			
.016	.017	306-336	.063	.070	252-281			
.017	.018	304-334	.070	.075	250-278			
.018	.020	300-330	.075	.080	246-275			
.020	.022	296-328	.080	.087	242-271			
.022	.024	292-322	.087	.095	238-268			
.024	.026	291-320	.095	.105	232-262			
.026	.028	289-318	.105	.115	227-257			
.028	.031	285-315	.115	.125	222-253			

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs if you have any questions.



# Technical Data Sheet

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs if you have any questions.

**Gibbs Wire & Steel Company Inc.**  
**Metals Drive, Southington, CT 06489 (860) 621-0121**

**No. 1001-N 01/14**