

TYPE 316 STAINLESS STEEL STRIP

Type 316, ASTM-A666 stainless steel strip are molybdenum bearing stainless steels possessing a greatly increased resistance to chemical attack as compared to that of the basic chromium-nickel analysis. In addition, Type 316 also offers higher creep, stress-to-rupture, and tensile strengths at elevated temperatures than any other stainless steel. Gibbs Interwire stocks this material in gauges from .010" - .025" in the annealed and ¼ hard conditions.

Chemical Composition	%	Thickness Tolerances	Tolerance (inch)
Carbon	.080 max	over .050 - .062 included	+/- .0030
Manganese	2.00 max	over .035 - .050 included	+/- .0025
Silicon*	.75 - 1.00 max	over .020 - .035 included	+/- .0020
Phosphorus	.040 max	over .010 - .020 included	+/- .0015
Sulfur	.030 max	under .010	+/- 10%
Chromium	16.00 - 18.00		
Nickel	10.00 - 14.00		
Molybdenum*	2.00 – 3.00		
Copper*	.750 max		

*Per AMS Spec

MECHANICAL PROPERTIES

Condition	AMS Specification	Tensile Min PSI	Yield Min PSI	Elong % Min	Condition
Annealed	5524	75,000	30,000	40 / 45*	RB 95 max
¼ Hard	5907	125,000	75,000	10	RC 25 min

*.025 thickness and over

Additional Information		
Width Tolerance	+/- .003	
Camber Tolerance	Up to and including 1.500" wide	.500" in 8 feet
	Over 1.500" wide	.250" in 8 feet
Edges Available	#3 Slit edge	
	#5 Deburred edge	
	#1 Round edge	

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs Interwire if you have any questions.

Limitation of Liability and Disclaimer of Warranty:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed; however, Gibbs Interwire does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary. Gibbs Interwire makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Gibbs Interwire be liable for any damages whatsoever arising from the use of the information included in the data sheets.

