

INCONEL X750 SPRING TEMPER WIRE

Inconel X750 is a precipitation-hardenable nickel-chromium alloy used for its corrosion and oxidation resistance and high strength at temperatures to 1300°F. Wire is available in size ranges from .020" - .625". Meets AMS 5699.

Chemical Composition Per AMA-5699	%		Chemical Composition	%
Nickel	70.00 min		Manganese	1.00 max
Chromium	14.00 – 17.00		Silicon	.50 max
Iron	5.00 – 9.00		Sulfur	.010 max
Titanium	2.25 – 2.75		Copper	.50 max
Aluminum	.40 – 1.00		Carbon	.080 max
Columbium	.70 – 1.20		Cobalt	1.00 max
Tantalum	.050 max			

Tensile Strength Table (AMS-5699)

Diameter Inch.		Tensile
Up to .250 included		190,000 psi min
Over .250 to .625 included		160,000 psi min

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs Interwire if you have any questions.

Limitation of Liability and Disclaimer of Warranty:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design. Applications may be discussed; however, Gibbs Interwire does not recommend or endorse any material for any particular end use or application. The data included in this data sheet are typical values and may vary. Gibbs Interwire makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet. In no event will Gibbs Interwire be liable for any damages whatsoever arising from the use of the information included in the data sheets.