

## TYPE 302 STAINLESS STEEL WIRE

Type 302 stainless steel wire is a general-purpose stainless alloy typically composed of 18% chromium and 8% nickel. The balance of the chemistry is: carbon 15% maximum, manganese 2% maximum: and silicon 1% maximum. It is the most widely used stainless spring wire because of its high corrosion resistance properties and good tensile strength. For spring applications, it is generally furnished in the cold drawn condition. The tensile strength for straightened and cut wire may be reduced by 10% from the figures shown on the table. However, material in the spring condition is slightly magnetic due to the transformation of some martinsite in the drawing operation. The greater the amount of cold reduction the higher the degree of magnetism. Gibbs Interwire Type 302 stainless steel wire is available in the size range .006" to .625". All wire conforms to ASTM-A-313 and AMS-5688.

Chemical Composition Per ASTM-A-313					
Carbon	.120%	Silicon	1.00%	Nickel	8.00 – 10.00%
Manganese	2.00%	Sulfur	.030%	Nitrogen	.10%
Phosphorus	.045%	Chromium	17.00 – 19.00%	Molybdenum*	.750%
Copper*	.750%				
*AMS 5688					

## TENSILE STRENGTH TABLE (ASTM-A-313)

Diameter		Tensile KSI	Diameter		Tensile KSI	Diameter		Tensile KSI
Over	To		Over	To		Over	To	
.001	.008	325-355	.031	.034	282-310	.125	.136	217-248
.009	.010	320-350	.034	.037	280-308	.136	.148	210-241
.010	.011	318-348	.037	.041	275-304	.148	.162	205-235
.011	.012	316-346	.041	.045	272-300	.162	.177	198-228
.012	.013	314-344	.045	.050	267-295	.177	.192	194-225
.013	.014	312-342	.050	.054	265-293	.192	.207	188-220
.014	.015	310-340	.054	.058	261-289	.207	.225	182-214
.015	.016	308-338	.058	.063	258-285	.225	.250	175-205
.016	.017	306-336	.063	.070	252-281	.250	.278	168-198
.017	.018	304-334	.070	.075	250-278	.278	.306	161-192
.018	.020	300-330	.075	.080	246-275	.306	.331	155-186
.020	.022	296-328	.080	.087	242-271	.331	.362	150-180
.022	.024	292-322	.087	.095	238-268	.362	.394	145-175
.024	.026	291-320	.095	.105	232-262	.394	.438	140-170
.026	.028	289-318	.105	.115	227-257	.438	.500	135-165
.028	.031	285-315	.115	.125	222-253	.500	.625	130-160

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs Interwire if you have any questions.

### Limitation of Liability and Disclaimer of Warranty:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design. Applications may be discussed; however, Gibbs Interwire does not recommend or endorse any material for any particular end use or application. The data included in this data sheet are typical values and may vary. Gibbs Interwire makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet. In no event will Gibbs Interwire be liable for any damages whatsoever arising from the use of the information included in the data sheets.

### Locations in the USA, Canada, & Mexico