

TYPE 17 CHROME - 7 NICKEL STAINLESS STEEL STRIP

Type 17-7 PH, "Condition C" has the corrosion resistance of Type 302 plus superior strength and heat resistance. After forming, it can be heat treated at 900 F for one hour to achieve maximum "CH" tensile strength.

Chemical Composition	%	Thickness Tolerances < 6" AMS2242	Tolerance (inch)
Carbon	.090 max	over .050 - .062 included	+/- .0030
Manganese	1.00 max	over .035 - .050 included	+/- .0025
Silicon	1.00 max	over .020 - .035 included	+/- .0020
Chromium	16.00 – 18.00	over .010 - .020 included	+/- .0015
Aluminum	0.75 – 1.50	under .010	+/- 10%
Nickel	6.5 – 7.75		

MECHANICAL PROPERTIES

Condition	Tensile Min PSI	Yield Min PSI	Elong % Min	Hardness (Ref Only)	Condition
"C"	200,000 min	175,000 min	1% min	RC 41	"C"
"CH 900"	240,000 min	230,000 min	1% min	RC 46	"CH 900"

Additional Information		
Width Tolerance	+/- .003	
Camber Tolerance	Up to and including 1.500" wide	.500" in 8 feet
	Over 1.500" wide	.250" in 8 feet
Edges Available	#3 Slit edge	
	#5 Deburred edge	
	#1 Round edge	

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs Interwire if you have any questions.

Limitation of Liability and Disclaimer of Warranty:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed; however, Gibbs Interwire does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary. Gibbs Interwire makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Gibbs Interwire be liable for any damages whatsoever arising from the use of the information included in the data sheets.

