

TYPE C1074 CARBON STEEL STRIP

This steel is most often used for general spring applications. Gibbs Interwire stocks 1074 high carbon spring steel, ASTM-A684, in both the spheroidized annealed condition and scaleless tempered condition.

Chemical Composition	%	Thickness Tolerances < 6" AMS2242	Tolerance (inch)
Carbon	.700 to .800	.001 - .0099	+/- .0003
Manganese	.500 to .800	.010 - .0149	+/- .0005
Phosphorus	.030 max	.015 - .0199	+/- .0008
Sulfur	.035 max	.020 - .0299	+/- .0010
Silicon	.150 to .300	.030 - .0399	+/- .0012
		.040 - .062	+/- .0014

MECHANICAL PROPERTIES

Condition	Hardness
Spheroidized Annealed	85 HRB Max

Additional Information		
Width Tolerance	+/- .003	
Camber Tolerance	Up to and including 1.500" wide	.500" in 8 feet
	Over 1.500" wide	.250" in 8 feet
Edges Available	#3 Slit edge	
	#5 Deburred edge	
	#1 Round edge	

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs Interwire if you have any questions.

Limitation of Liability and Disclaimer of Warranty:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design.

Applications may be discussed; however, Gibbs Interwire does not recommend or endorse any material for any particular end use or application.

The data included in this data sheet are typical values and may vary. Gibbs Interwire makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet.

In no event will Gibbs Interwire be liable for any damages whatsoever arising from the use of the information included in the data sheets.

