

## TYPE PHOSPHOR BRONZE STRIP

Alloy 510 Phosphor bronze strip, ASTM-B-103, offers excellent corrosion resistance and good strength and electrical conductivity. Gibbs Interwire stocks Grade A phosphor bronze in spring temper (8#s hard ) in the RB 94- 98 Rockwell range. Call for availability.

Chemical Composition Per ASTM-B-159			Dimensional Tolerances	Tolerance (inch)
Tin	4.20 – 5.80%		Over .004 - .006 included	+ / - .0006
Phosphorus	.03 – .35%		Over .006 - .009 included	+ / - .0008
Iron	.10% max		Over .009 - .013 included	+ / - .0010
Lead	.05% max		Over .013 - .017 included	+ / - .0013
Zinc	.30% max		Over .017 - .021 included	+ / - .0015
Copper	remainder		Over .021 - .026 included	+ / - .0020
			Over .026 - .037 included	+ / - .0025

## TENSILE STRENGTH TABLE (ASTM-B-103)

Condition	Tensile PSI	Hardness
Full Hard	95,000 – 110,000	RB 94 - 98

The above charts are intended to provide general background information. You should also review the appropriate material specification. Please contact Gibbs Interwire if you have any questions.

### Limitation of Liability and Disclaimer of Warranty:

The content in these data sheets is provided primarily by third-party melting mills and is provided for reference only. It is not intended for engineering or design. Applications may be discussed; however, Gibbs Interwire does not recommend or endorse any material for any particular end use or application. The data included in this data sheet are typical values and may vary. Gibbs Interwire makes no representations or warranties, express or implied, as to the accuracy, completeness, condition, suitability, performance, fitness for a particular purpose, or merchantability of any information contained in any data sheet. In no event will Gibbs Interwire be liable for any damages whatsoever arising from the use of the information included in the data sheets.